

(19)



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 1 165 696 B1**

(12)

**EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention  
of the grant of the patent:  
12.03.2003 Bulletin 2003/11

(51) Int Cl.7: **C09B 67/22, D21H 21/28**

(86) International application number:  
**PCT/EP00/02955**

(21) Application number: **00920655.8**

(87) International publication number:  
**WO 00/061689 (19.10.2000 Gazette 2000/42)**

(22) Date of filing: **03.04.2000**

**(54) PIGMENT COMPOSITIONS AND PROCESS OF SHADING**

PIGMENTZUSAMMENSETZUNGEN UND ABTÖNUNGSVERFAHREN

COMPOSITIONS DE PIGMENTS ET PROCEDE DE COLORATION

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE**

(30) Priority: **08.04.1999 GB 9907878**

(43) Date of publication of application:  
**02.01.2002 Bulletin 2002/01**

(73) Proprietors:  
• **Ciba Specialty Chemicals Holding Inc.  
4057 Basel (CH)**  
• **Stora Kopparbergs Bergslags AB  
S-791 80 Falun (SE)**

(72) Inventors:  
• **KNOWLES, Ian, William  
Stockport, Cheshire SK4 5HH (GB)**  
• **WATSFELDT, Robert  
427 37 Billdal (SE)**  
• **KUMLIN, Kjell, Erik  
652 30 Karlstad (SE)**

(56) References cited:  
**EP-A- 0 632 108 EP-A- 0 654 506**  
**FR-A- 941 218 FR-A- 2 084 891**  
**GB-A- 2 071 683 US-A- 2 844 485**  
**US-A- 3 074 950 US-A- 5 131 981**  
**US-A- 6 033 444**

**EP 1 165 696 B1**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

## Description

[0001] The present invention relates to compositions comprising special pigments which meet BGVV specifications for food packaging materials.

5 [0002] It is the object of the present invention to provide a pigment composition which can be used for the shading of food packaging materials, especially such materials which are made of paper.

[0003] In one aspect, the invention relates to a composition comprising

- 10 a) a mixture of C.I. Pigment Violet 19 together with either C.I. Pigment Blue 15 or C.I. Pigment Blue 60,
- b) a dispersant,
- c) optionally a biocide, and
- d) water.

[0004] One preferred form of this composition comprises a mixture of C.I. Pigment Violet 19 together with C.I. Pigment Blue 15, in which mixture the amount by weight of C.I. Pigment Violet 19 is greater than 50%, based on the weight of the mixture of pigments. The mixture of pigments contains usually 60% to 95% by weight, preferably 70% to 90% by weight, of C.I. Pigment Violet 19, based on the weight of the mixture of pigments. Particularly preferred are compositions wherein the mixture of pigments contains 75% to 85 % by weight of C.I. Pigment Violet 19 and 15% to 25 % by weight of C.I. Pigment Blue 15.

20 [0005] A further preferred form of this composition comprises a mixture of C.I. Pigment Violet 19 together with C.I. Pigment Blue 15 or C.I. Pigment Blue 60, in which mixture the amount by weight of C.I. Pigment Violet 19 is less than 50%, based on the weight of the mixture of pigments. Particularly preferred compositions comprise a mixture of pigments containing C.I. Pigment Violet 19 together with C.I. Pigment Blue 60. The mixture of pigments contains usually 30% to less than 50 % by weight, preferably 40% to less than 50 % by weight of C.I. Pigment Violet 19, based on the weight of the mixture of pigments.

25 [0006] In a second aspect, this invention relates to a composition comprising

- 30 a) a mixture of C.I. Pigment Red 177 together with C.I. Pigment Blue 15 or C.I. Pigment Blue 60,
- b) a dispersant,
- c) optionally a biocide, and
- d) water.

[0007] Particularly preferred are compositions that include a mixture of pigments containing C.I. Pigment Red 177 together with C.I. Pigment Blue 60. The mixture of pigments contains usually below 60 % by weight, preferably below 35 50 % by weight of C.I. Pigment Red 177, based on the weight of the mixture of pigments. Highly preferred are mixtures of pigments which contain 20 or 25 to 40 % by weight of C.I. Pigment Red 177 and 60 to 75 % by weight of C.I. Pigment Blue 60.

[0008] The compositions in all aspects of the invention contain preferably 0.1 to 40%, more preferably 10 to 30 % of pigments, most preferably around 20% of pigments, based on the weight of the composition.

40 [0009] The size of the pigments can range from a few nanometres to several hundreds of microns. Preferred is an average size distribution of 0.01 to 1 micron.

[0010] The dispersant usually is present in the composition in an amount of 0.1 to 30%, preferably 0.1 to 8% by weight, most preferably 3 to 6%, based on the weight of the composition.

45 [0011] Preferred dispersants are for example polyacrylic acid, polymethacrylic acid, polymaleic anhydride, polyurethane, polyvinylether, polyvinylalcohol, polyalkylene glycol, polyethylene oxide, cellulose derivatives, polyimine, polyvinylpyridine, or copolymers thereof, or copolymers such as copolymers of acrylic acid with styrene, acrylonitrile, vinylacetate, vinylphosphonate, vinylpropionate, vinylchloride, itaconic acid or maleic anhydride, or a mixture thereof. Suitable polymeric derivatives are for example ethoxylated or propoxylated fatty amines such as ethoxylated cocoalkyl, oleyl or soyaalkyl amines; ethoxylated or propoxylated fatty quaternary salts such as ethoxylated cocoalkyltrimethyl ammonium chloride; ethoxylated fatty amides such as ethoxylated oleamides; alkyl-, cycloalkyl- or alkylaryl-oxypoly (ethylenoxy)ethanol, cycloalkyloxypoly(ethylenoxy)laurate or oleate, polyethylene glycol 400 laurate or oleate, alkyl-, cycloalkyl- or alkylaryl-poly(ethylenoxy)carboxylate or phosphonate. An especially preferred cycloalkyloxypoly(ethylenoxy) laurate or oleate is for example a poly(ethylenoxy)sorbitan laurate or oleate. Particularly preferred dispersants include polymers of aromatic sulphonic acids with formaldehyde, and salts thereof. Typically the dispersants have 55 molecular weights in the range 1000 to 10,000, preferably 2,000 to 5,000, especially 2,500 to 3,500. These preferably water-soluble polymers, copolymers and/or polymer derivatives are known per se and are commercially available.

[0012] Preferably, the compositions contain a biocide. All FDA and BGVV compliant biocides are suitable for this application. Any of such biocide capable of inhibiting the growth of either or all of Gram positive or Gram negative

bacteria, yeasts or fungi may be employed according to the present invention. Suitable biocides include thiazol-3-one derivatives, for instance alkyl and/or chlorinated derivatives of thiazol-3-one or mixtures thereof. Typically the biocide is present at levels of from about 15 parts per million (ppm) by weight of the composition to about 1000 ppm, most preferably from about 50 ppm to about 500 ppm by weight of the composition.

5 [0013] A further object of the present invention is to provide a process for the shading of paper wherein either of the above compositions or separate dispersions of said constituent pigments are applied to at least one stage of the paper making process.

[0014] Thus one aspect of the invention relates to a process for shading of paper to be used for food packaging material, which process comprises applying to at least one stage of the paper making process either

10

a) a composition comprising

i) a mixture of C.I. Pigment Violet 19 together with C.I. Pigment Blue 15,

ii) a dispersant,

15

iii) optionally a biocide, and

iv) water.

or

b) an aqueous dispersion of C.I. Pigment Violet 19 and an aqueous dispersion of C.I. Pigment Blue 15.

20

[0015] The aqueous pigment dispersions of C.I. Pigment Violet 19 comprises,

a) C.I. Pigment Violet 19,

b) a dispersant,

25

c) optionally a biocide, and

d) water.

[0016] The aqueous pigment dispersion of C.I. Pigment Blue 15 comprises,

30

a) C.I. Pigment Blue 15,

b) a dispersant,

c) optionally a biocide, and

d) water.

35

[0017] The preferences given before for the compositions also apply to the process for applying the compositions.

[0018] In one preferred form of the process of shading paper, a dispersion of C.I. Pigment Violet 19 and a dispersion of C.I. Pigment Blue 15 are applied to at least one stage of the paper making process, wherein the C.I. Pigment 19 is added in an amount of greater than 50% by weight of added pigments. The C.I. Pigment 19 is usually added in an amount of 60% to 95% by weight, preferably 70% to 90% by weight of the added pigments. In a particularly preferred form of the process C.I. Pigment Violet 19 is added in an amount of 75% to 85 % by weight and C.I. Pigment Blue 15 is added in an amount of 15% to 25 % by weight of C.I. Pigment Blue 15 based on the weight of the added pigments.

40

[0019] In another preferred form of the process a dispersion of C.I. Pigment Violet 19 and a dispersion of either C.I. Pigment Blue 15 or C.I. Pigment Blue 60 are added to at least one stage of the paper making process, wherein amount of C.I. Pigment Violet 19 used is less than 50% of the total amount of pigment used. The amount of C.I. Pigment Violet 19 used is usually 30% to less than 50 % by weight, preferably 40% to less than 50 % by weight, based on the weight of the pigments used.

45

[0020] A further aspect of the process of the invention relates to a process for shading of paper to be used for food packaging material, which process comprises applying at least one stage of the paper making process either

50

a) a composition comprising,

i) a mixture of C.I. Pigment Red 177 together with C.I. Pigment Blue 15 or C.I. Pigment Blue 60,

ii) a dispersant,

iii) optionally a biocide, and

55

iv) water,

or

b) an aqueous dispersion of C.I. Pigment Red 177 and an aqueous dispersion of either C.I. Pigment Blue 15 or

C.I. Pigment Blue 60.

[0021] The aqueous pigment dispersions of C.I. Pigment Red 177 comprises,

- 5 a) C.I. Pigment Red 177,
- b) a dispersant,
- c) optionally a biocide, and
- d) water.

10 [0022] The aqueous pigment dispersion of C.I. Pigment Blue 15 or C.I. Pigment Blue 60 comprises,

- a) C.I. Pigment Blue 15 or C.I. Pigment Blue 60,
- b) a dispersant,
- c) optionally a biocide, and
- 15 d) water.

[0023] In the process of shading paper in which a dispersion of C.I. Pigment Red 177 and a dispersion of either C.I. Pigment Blue 60 or C.I. Pigment Blue 15 is added to at least one stage of the paper making process, C.I. Pigment Red 177 is usually added in an amount below 60 % by weight, preferably below 50% by weight, of the added pigments. In a particularly preferred process C.I. Pigment Red 177 is added in an amount of 20 or 25 to 40 % by weight, based on the weight of added pigments and C.I. Pigment Blue 15 or C.I. Pigment Blue 60 is added in an amount of 60 to 75 % by weight of the added pigments.

[0024] When separate pigment dispersions are applied to the process it is possible for the aqueous pigment dispersions to be added at different stages of the paper making process, though best results are usually obtained if the pigment dispersions are added to the same stage. As for the combined pigment compositions the separate aqueous pigment dispersions contain preferably 0.1 to 40%, more preferably 10 to 30%, most preferably around 20% of the respective pigment, based on the weight of the dispersion. Generally the amounts of dispersants and biocides used in each of the aqueous pigment dispersions would be substantially the same as the amounts used in the composition given before.

[0025] According to conventional paper making processes the pulp is processed in a mixing chest where it is mixed in a conventional manner to form a thick stock, which is then diluted to form the thin stock, the thin stock is passed towards a drainage screen through various items of apparatus such as a fan pump and a centri screen, and the thin stock is drained through a screen so as to form a sheet, which is then dried. Such conventional processes are described, for example, in US-A-5,676,796.

35 [0026] For example, the composition can be added to the pulp, the mixing chest, the thick stock or the thin stock.

[0027] Whether the pigments are added in the form of the composition or in the form of separate pigment dispersions they are as a rule added in an amount of 5 to 1000 g per tonne, preferably in an amount of 10 to 400 g/tonne and most preferably in an amount of 50 or 100 to 400 g/tonne. The gram hereby refers to equivalent total dry weight of pigment added and the tonne hereby refers to the equivalent dry weight of material the composition or pigment dispersions are added to (for example the pulp).

[0028] In addition, at one of the stages of the paper making process a cationic coagulant or cationic retention aid can be added.

[0029] Preferably, the cationic coagulant is added prior to dilution, most preferably to the thick stock.

45 [0030] The coagulant usually is added in an amount of 10 to 1000 g/tonne, preferably in an amount of 50 to 700 g/tonne and most preferably in an amount of 100 to 500 g/tonne. The tonne hereby refers to the material the composition is added to (for example the thick stock).

[0031] Typical examples of coagulants are polyamine epichlorohydrin, polyethylene imine, polymers of cationic monomers such as diallyl dimethyl ammonium chloride, dialkyl aminoalkyl (meth)acrylates or quaternary ammonium salts, dialkyl aminoalkyl (meth)acrylamides or quaternary ammonium salts. Preferred are coagulants which have an intrinsic viscosity (IV) of below 3 dl/g and a cationic charge density of at least 4 meq/g.

50 [0032] The cationic retention aid may be the same polymer as the cationic coagulant or more usually is either cationic starch or a copolymer of cationic monomers such as diallyl dimethyl ammonium chloride, dialkyl aminoalkyl (meth)acrylates or quaternary ammonium salts, dialkyl aminoalkyl (meth)acrylamides or quaternary ammonium salts with nonionic monomers such as acrylamide. Typically the cationic retention aids are synthetic polymers which have which have an intrinsic viscosity (IV) of at least 3dl/g, usually at least 4 or 5 dl/g and can be as high as 10 or 12 dl/g or higher. Typically the cationic retention aids can have a cationic charge density of below 4 meq/g, preferably below 3 meq/g,

[0033] Another object of the present invention is the use of the inventive composition for shading of paper to be used for food packaging material.

[0034] The paper may be filled or unfilled paper and may be lightweight or heavyweight. The paper may be, for instance, paper board.

[0035] The special combination of pigments used according to the present invention allows shading of food packaging materials in a good manner. Especially for paper materials a very good whiteness is obtained.

[0036] These dispersions are suited for direct food contact packaging, eliminating the need for overwrapping foods. (Color additive petition for paper and board is pending. ) The food can be in liquid form as well as in solid form.

[0037] Furthermore, the dispersions are stable for a longer period of time and can therefore be stored before application, without showing deposits resulting in deteriorous application properties.

[0038] The following examples illustrate various embodiments of the invention, but the scope of the invention is not limited thereto. In the examples, percentages are by weight, unless otherwise indicated.

Example 1:

[0039] By mixing the following dispersion is prepared:

16 wt%	C.I. Pigment Violet 19
4 wt%	C.I. Pigment Blue 15
5.6 wt%	2-naphthalene sulphonic acid polymer with formaldehyde, sodium salt
0.008 wt%	5-chloro-2-methyl-2H-isothiazol-3-one
0.003 wt%	2-methyl- 2H-isothiazol-3-one.
74.389 wt%	water

Examples 2 to 5:

[0040] To a pulp comprising an elemental chlorine free blend of 70% bleached hardwood and 30% bleached softwood, 10% by weight of a filler (calcium carbonate) and 1.5% of a conventional sizing agent (Keydime C), the pulp having a pH of about 7.2, are added the dispersions given in the following Table 1 (the amounts given in Table 1 are given in % by weight, based on the weight of the pulp):

Table 1

Example	Amount of the dispersion of Example 1 (based on the weight of the pulp)
2	100 g/tonne
3	200 g/tonne
4	300 g/tonne
5	500 g/tonne

[0041] The pulp is processed further according to conventional methods, which means in the mixing chest the pulp is mixed in a conventional manner to form a thick stock, which is then diluted to form the thin stock, the thin stock is passed towards a drainage screen through various items of apparatus such as a fan pump and a centri screen, and draining the thin stock through a screen so as to form a sheet, which is then dried. In each case a paper is obtained which shows very good whiteness.

Example 6:

[0042] The above Example 4 is repeated, except that just prior to diluting the thick stock 300 g/tonne of a coagulant (Nalco 7607) is added. A paper is obtained which shows very good whiteness.

Example 7:

[0043] By mixing the dispersions given in the following Table 2 are prepared:

# EP 1 165 696 B1

Table 2

Dispersion	Violet Pigment	Blue Pigment	Dispersant	*Biocide	Water
A1	9.8 % of C.I. Pigment Violet 19	10.2 % of C.I. Pigment Blue 60	5.6 % of 2-naphthalene sulphonic acid polymer with formaldehyde, sodium salt	0.008 % of CMITO and 0.003 % of MITO	Water made up to 100%
B1	4.9 % of C.I. Pigment Violet 19	5.1 % of C.I. Pigment Blue 15	5.6 % of 2-naphthalene sulphonic acid polymer with formaldehyde, sodium salt	0.008 % of CMITO and 0.003 % of MITO	Water made up to 100%

\*The biocide CMITO is 5-chloro-2-methyl-2H-isothiazol-3-one and MITO is 2-methyl-2H-isothiazol-3-one.

## Examples 8 to 15:

[0044] To a pulp comprising an elemental chlorine free blend of 70% bleached hardwood and 30% bleached softwood, 10% by weight of a filler (calcium carbonate) and 1.5% of a conventional sizing agent (Keydime C), the pulp having a pH of about 7.2, are added the dispersions given in the following Table 2 (the amounts given in Table 2 are given in % by weight, based on the weight of the pulp):

Table 3

Example	Dispersion	Amount of the dispersion based on the weight of the pulp
8	A1	100 g/tonne
9	A1	200 g/tonne
10	A1	300 g/tonne
11	A1	500 g/tonne
12	B1	100 g/tonne
13	B1	200 g/tonne
14	B1	300 g/tonne
15	B1	500 g/tonne

[0045] The pulp is processed further according to conventional methods, which means in the mixing chest the pulp is mixed in a conventional manner to form a thick stock, which is then diluted to form the thin stock, the thin stock is passed towards a drainage screen through various items of apparatus such as a fan pump and a centri screen, and draining the thin stock through a screen so as to form a sheet, which is then dried. In each case a paper is obtained which shows very good whiteness.

## Examples 16 and 17:

[0046] Each of the above Examples 10 and 14 are repeated, except that just prior to diluting the thick stock 300 g/tonne of a coagulant (Nalco 7607) is added. In each case a paper is obtained which shows very good whiteness.

## Example 18:

[0047] By mixing the following dispersions of C.I Pigment Red 177, C.I. Pigment Blue 15 and Pigment Blue 60 are prepared:

C.I. Pigment Red 177 Dispersion	
19.9%	C.I. Pigment Red 177
4.0%	2-Naphthalene sulphonic acid, polymer with formaldehyde, sodium salt
0.008%	5-Chloro-2-methyl-2H-isothiazol-3-one
0.003%	2-Methyl-2H-isothiazol-3-one
79.089%	Water

C.I. Pigment Blue 60 Dispersion	
19.6%	C.I. Pigment Blue 60
5.74%	2-Naphthalene sulphonic acid, polymer with formaldehyde, sodium salt
0.008%	5-Chloro-2-methyl-2H-isothiazol-3-one
0.003%	2-Methyl-2H-isothiazol-3-one
79.649%	Water

C.I. Pigment Blue 15 Dispersion	
18.50%	C.I. Pigment Blue 15
5.60%	2-Naphthalene sulphonic acid, polymer with formaldehyde, sodium salt
0.008%	5-Chloro-2-methyl-2H-isothiazol-3-one
0.003%	2-Methyl-2H-isothiazol-3-one
75.889%	Water

#### Examples 19 to 22:

[0048] To a thick stock comprising an elemental chlorine free blend of 70% bleached hardwood and 30% bleached softwood, 10% by weight of a filler (calcium carbonate) and 1.5% of a conventional sizing agent (Keydime C), the pulp having a pH of about 7.2, pigment dispersions are added to the thick stock at doses given in Table 4 based .

Table 4

Example	C.I. Pigment Red177 Dispersion	C.I. Pigment Blue 60 Disperison	C.I. Pigment Blue 15 Disperion
19	60 g/ tonne	200 g/tonne	-
20	20g/tonne	66 g/tonne	-
21	6g/tonne	20 g/tonne	-
22	114g/tonne	-	86g/tonne

[0049] The pulp is processed further according to conventional methods, which means in the mixing chest the pulp is mixed in a conventional manner to form a thick stock, which is then diluted to form the thin stock, the thin stock is passed towards a drainage screen through various items of apparatus such as a fan pump and a centri screen, and draining the thin stock through a screen so as to form a sheet, which is then dried. In each case a paper is obtained which shows very good whiteness.

#### Examples 23 and 24:

[0050] Each of the above Examples 19 and 22 is repeated, except that just prior to diluting the thick stock 300 g/tonne of a coagulant (Nalco 7607) is added. In each case a paper is obtained which shows very good whiteness.

#### Claims

1. A composition comprising

EP 1 165 696 B1

- a) a mixture of C.I. Pigment Violet 19 together with either C.I. Pigment Blue 15 or C.I. Pigment Blue 60,  
b) a dispersant,  
c) optionally a biocide, and  
d) water.
- 5
2. A composition according to claim 1 wherein component a) comprises a mixture of C.I. Pigment Violet 19 together with C.I. Pigment Blue 15, in which mixture the amount by weight of C.I. Pigment Violet 19 is greater than 50%, based on the weight of the mixture of pigments.
- 10
3. A composition according to claim 1 or claim 2, wherein the mixture of pigments contains 60% to 95% by weight of C.I. Pigment Violet 19.
4. A composition according to any one of claims 1 to 3, wherein the mixture of pigments contains 70% to 90% by weight of C.I. Pigment Violet 19.
- 15
5. A composition according to any one of claims 1 to 4, wherein the mixture of pigments contains 75% to 85% by weight of C.I. Pigment Violet 19 and 15% to 25% by weight of C.I. Pigment Blue 15.
- 20
6. A composition according to claim 1 wherein component a) comprises a mixture of C.I. Pigment Violet 19 together with C.I. Pigment Blue 15 or C.I. Pigment Blue 60, in which mixture the amount by weight of C.I. Pigment Violet 19 is less than 50%, based on the weight of the mixture of pigments,
- 25
7. A composition according to claim 6, wherein the mixture of pigments contains C.I. Pigment Violet 19 together with C.I. Pigment Blue 60.
8. A composition according to claim 6 or claim 7, wherein the mixture of pigments contains 30% to less than 50 % by weight of C.I. Pigment Violet 19.
- 30
9. A composition according to any one of claim 6 to claim 8, wherein the mixture of pigments contains 40% to less than 50 % by weight of C.I. Pigment Violet 19.
10. A composition comprising
- 35
- a) a mixture of C.I. Pigment Red 177 together with C.I. Pigment Blue 15 or C.I. Pigment Blue 60,  
b) a dispersant,  
c) optionally a biocide, and  
d) water.
- 40
11. A composition according to claim 10, wherein the mixture of pigments contains C.I. Pigment Red 177 together with C.I. Pigment Blue 60.
12. A composition according to claim 10 or claim 11, wherein the mixture of pigments contains below 60 % by weight of C.I. Pigment Red 177.
- 45
13. A composition according to any one of claims 10 to 12, wherein the mixture of pigments contains below 50 % by weight of C.I. Pigment Red 177.
14. A composition according to any one of claims 10 to 13, wherein the mixture of pigments contains 25 to 40 % by weight of C.I. Pigment Red 177 and 60 to 75 % by weight of C.I. Pigment Blue 60.
- 50
15. A composition according to any one of claims 1 to 14, which contains 0.1 to 40%, more preferably 10 to 30 %, most preferably around 20% pigment, based on the weight of the dispersion.
- 55
16. A composition according to any one of claims 1 to 15, which contains 0.1 to 30%, preferably 0.1 to 8% of dispersant, by weight of the composition.



17. A composition according to any one of claims 1 to 16, which contains a biocide.
18. A composition according to any one of claims 1 to 17, wherein the dispersant is polyacrylic acid, polymethacrylic acid, polymaleic anhydride, polyurethane, polyvinylether, polyvinylalcohol, polyalkylene glycol, polyethylene oxide, cellulose derivatives, polyimine, polyvinylpyridine, or copolymers thereof, or copolymers of acrylic acid with styrene, acrylonitrile, vinylacetate, vinylphosphonate, vinylpropionate, vinylchloride, itaconic acid or maleic anhydride, or ethoxylated or propoxylated fatty, ethoxylated or propoxylated fatty quaternary salts, ethoxylated fatty amides, alkyl-, cycloalkyl- or alkylaryl-oxy poly(ethylenoxy)ethanol, cycloalkyloxypoly(ethylenoxy)laurate or oleate, polyethylene glycol 400 laurate or oleate, alkyl-, cycloalkyl- or alkylaryl-poly(ethylenoxy)carboxylate or phosphonate or aromatic sulphonic acid polymer with formaldehyde or salts thereof.
19. A process for shading of paper to be used for food packaging material, which process comprises applying to at least one stage of the paper making process either
- a composition according to claim 1,
  - a composition according to claim 10,
  - an aqueous dispersion of C.I. Pigment Violet 19 and an aqueous dispersion of C.I. Pigment Blue 15, or
  - an aqueous dispersion of C.I. Pigment Red 177 and an aqueous dispersion of either C.I. Pigment Blue 15 or C.I. Pigment Blue 60.
20. A process according to claim 19, wherein the composition is added to the mixing chest, the thin stock, the thick stock or preferably to the pulp.
21. A process according to claim 19 or claim 20, wherein the composition is added in an amount of 5 to 1000 g per tonne, preferably in an amount of 10 to 400 g/tonne and most preferably in an amount of 50 to 400 g/tonne.
22. A process according to any one of claims 19 to 21, wherein in addition a cationic coagulant or retention aid is added.
23. A process according to claim 22, wherein the cationic coagulant is added to the thick stock, preferably prior to dilution.
24. A process according to claim 23, wherein the cationic coagulant is added in an amount of 10 to 1000 g per tonne, preferably in an amount of 50 to 700 g/tonne and most preferably in an amount of 100 to 500 g/tonne.
25. Use of a composition according to claim 1 or claim 10 for shading of paper to be used for food packaging material.

#### Patentansprüche

- Zusammensetzung, umfassend
  - eine Mischung von C.I.-Pigment-Violet-19 zusammen mit entweder C.I.-Pigment-Blue-15 oder C.I.-Pigment-Blue-60,
  - ein Dispergierungsmittel,
  - wahlweise ein Biozid und
  - Wasser.
- Zusammensetzung nach Anspruch 1, worin Komponente a) eine Mischung von C.I.-Pigment-Violet-19 zusammen mit C.I.-Pigment-Blue-15 umfasst, worin in der Mischung die Menge bezogen auf das Gewicht von C.I.-Pigment-Violet-19 größer als 50% ist, auf der Basis des Gewichts der Mischung der Pigmente.
- Zusammensetzung nach Anspruch 1 oder Anspruch 2, worin die Mischung der Pigmente 60 Gew.-% bis 95 Gew.-% C.I.-Pigment-Violet-19 enthält.
- Zusammensetzung nach mindestens einem der Ansprüche 1 bis 3, worin die Mischung der Pigmente 70 bis 90 Gew.-% C.I.-Pigment-Violet-19 enthält.
- Zusammensetzung nach mindestens einem der Ansprüche 1 bis 4, worin die Mischung der Pigmente 75 Gew.-%

## EP 1 165 696 B1

bis 85 Gew.-% C.I.-Pigment-Violet-19 und 15 Gew.-% bis 25 Gew.-% C.I.-Pigment-Blue-15 enthält.

- 5 6. Zusammensetzung nach Anspruch 1, worin die Komponente a) eine Mischung von C.I.-Pigment-Violet-19 zusammen mit C.I.-Pigment-Blue-15 oder C.I.-Pigment-Blue-60 umfasst, worin in der Mischung der Anteil bezogen auf das Gewicht an C.I.-Pigment-Violet-19 geringer als 50% ist, auf der Basis des Gewichts der Mischung der Pigmente.
7. Zusammensetzung nach Anspruch 6, worin die Mischung der Pigmente C.I.-Pigment-Violet-19 zusammen mit C.I.-Pigment-Blue-60 enthält.
- 10 8. Zusammensetzung nach Anspruch 6 oder Anspruch 7, worin die Mischung der Pigmente 30 Gew.-% bis weniger als 50 Gew.-% C.I.-Pigment-Violet-19 enthält.
- 15 9. Zusammensetzung nach mindestens einem der Ansprüche 6 bis 8, worin die Mischung der Pigmente 40 Gew.-% bis weniger als 50 Gew.-% an C.I.-Pigment-Violet-19 enthält.
10. Zusammensetzung, umfassend
  - 20 a) ein Mischung von C.I.-Pigment-Red-177 zusammen mit C.I.-Pigment-Blue-15 oder C.I.-Pigment-Blue-60,
  - b) ein Dispergierungsmittel,
  - c) wahlweise ein Biozid,
  - d) Wasser.
- 25 11. Zusammensetzung nach Anspruch 10, worin die Mischung der Pigmente C.I.-Pigment-Red-177 zusammen mit C.I.-Pigment-Blue-60 enthält.
12. Zusammensetzung nach Anspruch 10 oder Anspruch 11, worin die Mischung der Pigmente weniger als 60 Gew.-% C.I.-Pigment-Red-177 enthält.
- 30 13. Zusammensetzung nach mindestens einem der Ansprüche 10 bis 12, worin die Mischung der Pigmente weniger als 50 Gew.-% C.I.-Pigment-Red-177 enthält.
14. Zusammensetzung nach mindestens einem der Ansprüche 10 bis 13, worin die Mischung der Pigmente 25 bis 40 Gew.-% C.I.-Pigment-Red-177 und 60 bis 75 Gew.-% C.I.-Pigment-Blue-60 enthält.
- 35 15. Zusammensetzung nach mindestens einem der Ansprüche 1 bis 14, welche 0,1 bis 40%, besonders bevorzugt 10 bis 30%, ganz besonders bevorzugt ungefähr 20 Gew.-% Pigment, auf der Basis des Gewichts der Dispersion, enthält.
- 40 16. Zusammensetzung nach mindestens einem der Ansprüche 1 bis 15, welche 0,1 bis 30%, bevorzugt 0,1 bis 8% Dispergierungsmittel, bezogen auf das Gewicht der Zusammensetzung, enthält.
17. Zusammensetzung nach mindestens einem der Ansprüche 1 bis 16, welche ein Biozid enthält.
- 45 18. Zusammensetzung nach mindestens einem der Ansprüche 1 bis 17, worin das Dispergierungsmittel Polyacrylsäure, Polymethacrylsäure, Polymaleinsäureanhydrid, Polyurethan, Polyvinylether, Polyvinylalkohol, Polyalkylen-glykol, Polyethylenoxid, Cellulosederivate, Polyimide, Polyvinylpyridin, oder Copolymere davon, oder Copolymere von Acrylsäure mit Styrol, Acrylnitril, Vinylacetat, Vinylphosphonat, Vinylpropionat, Vinylchlorid, Itaconsäure oder Maleinsäureanhydrid, oder ethoxylierte oder propoxylierte Fette, oder ethoxylierte oder propoxylierte quaternäre Fettsalze, ethoxylierte Fettamide, Alkyl-, Cycloalkyl- oder Alkylaryloxypoly(ethylenoxy)ethanol, Cycloalkyloxypoly(ethylenoxy)laurat oder -oleat, Polyethylenglykol-400-laurat oder -oleat, Alkyl- Cycloalkyl- oder Alkylaryl-poly(ethylenoxy)carboxylat oder -phosphonat oder aromatisches Sulfonsäurepolymer mit Formaldehyd oder Salze davon ist.
- 50 19. Verfahren zum Abtönen bzw. Nuancieren von Papier, welches als Nahrungsmittelverpackungsmaterial verwendet wird, wobei das Verfahren die Anwendung in mindestens einer Stufe des Paplerherstellungsverfahrens umfasst entweder
- 55

- a) einer Zusammensetzung nach Anspruch 1.
  - b) einer Zusammensetzung nach Anspruch 10,
  - c) einer wässrigen Dispersion von C.I.-Pigment-Violet-19 und einer wässrigen Dispersion von C.I.-Pigment-Blue-15 oder
  - d) einer wässrigen Dispersion von C.I.-Pigment-Red-177 und einer wässrigen Dispersion von entweder C.I.-Pigment-Blue-15 oder C.I.-Pigment-Blue-60.
20. Verfahren nach Anspruch 19, worin die Zusammensetzung zu dem Mischbehälter, dem dünnflüssigen Papierrohstoff, dem dickflüssigen Papierrohstoff oder bevorzugt der Pulpe zugesetzt wird.
21. Verfahren nach Anspruch 19 oder Anspruch 20, worin die Zusammensetzung in einer Menge von 5 bis 1000 g/t, bevorzugt in einer Menge von 10 bis 400 g/t und ganz besonders bevorzugt in einer Menge von 50 bis 400 g/t zugesetzt wird.
22. Verfahren nach mindestens einem der Ansprüche 19 bis 21, worin zusätzlich ein kationisches Koagulierungsmittel oder Retentionshilfsmittel zugesetzt wird.
23. Verfahren nach Anspruch 22, worin das kationische Koagulierungsmittel zu dem dickflüssigen Papierrohstoff, bevorzugt vor der Verdünnung, zugesetzt wird.
24. Verfahren nach Anspruch 23, worin das kationische Koagulierungsmittel in einer Menge von 10 bis 1000 g/t, bevorzugt in einer Menge von 50 bis 700 g/t und ganz besonders bevorzugt in einer Menge von 100 bis 500 g/t, zugesetzt wird.
25. Verwendung einer Zusammensetzung nach Anspruch 1 oder Anspruch 10 zum Abtönen bzw. Nuancieren von Papier, welches als Nahrungsmittelverpackungsmaterial verwendet wird.

# Revendications

1. Composition comprenant
- a) un mélange de Pigment Violet 19 du C.I. avec soit le Pigment Bleu 15 du C.I., soit le Pigment Bleu 60 du C.I.,
  - b) un dispersant,
  - c) facultativement un biocide, et
  - d) de l'eau.
2. Composition selon la revendication 1, dans laquelle le composant a) comprend un mélange de Pigment Violet 19 du C.I. avec le Pigment Bleu 15 du C.I., mélange dans lequel la quantité en poids de Pigment Violet 19 du C.I. est supérieure à 50 % par rapport au poids du mélange de pigments.
3. Composition selon la revendication 1 ou la revendication 2, dans laquelle le mélange de pigments contient 60 % à 95 % en poids de Pigment Violet 19 du C.I.
4. Composition selon l'une quelconque des revendications 1 à 3, dans laquelle le mélange de pigments contient 70 % à 90 % en poids de Pigment Violet 19 du C.I.
5. Composition selon l'une quelconque des revendications 1 à 4, dans laquelle le mélange de pigments contient 75 % à 85 % en poids de Pigment Violet 19 du C.I. et 15 % à 25 % en poids de Pigment Bleu 15 du C.I.
6. Composition selon la revendication 1, dans laquelle le composant a) comprend un mélange de Pigment Violet 19 du C.I. avec le Pigment Bleu 15 du C.I. ou le Pigment Bleu 60 du C.I., mélange dans lequel la quantité en poids de Pigment Violet 19 du C.I. est inférieure à 50 % par rapport au poids du mélange de pigments.
7. Composition selon la revendication 6, dans laquelle le mélange de pigments contient le Pigment Violet 19 du C.I. avec le Pigment Bleu 60 du C.I.
8. Composition selon la revendication 6 ou la revendication 7, dans laquelle le mélange de pigments contient 30 %

## EP 1 165 696 B1

à moins de 50 % en poids de Pigment Violet 19 du C.I.

- 5
9. Composition selon l'une quelconque des revendications 6 à 8, dans laquelle le mélange de pigments contient 40 % à moins de 50 % en poids de Pigment Violet 19 du C.I.
- 10
10. Composition comprenant
- a) un mélange de Pigment Rouge 177 du C.I. avec le Pigment Bleu 15 du C.I. ou le Pigment Bleu 60 du C.I.
  - b) un dispersant,
  - c) facultativement un biocide, et
  - d) de l'eau.
- 15
11. Composition selon la revendication 10, dans laquelle le mélange de pigments contient le Pigment Rouge 177 du C.I. avec le Pigment Bleu 60 du C.I.
12. Composition selon la revendication 10 ou la revendication 11, dans laquelle le mélange de pigments contient moins de 60 % en poids de Pigment Rouge 177 du C.I.
- 20
13. Composition selon l'une quelconque des revendications 10 à 12, dans laquelle le mélange de pigments contient moins de 50 % en poids de Pigment Rouge 177 du C.I.
14. Composition selon l'une quelconque des revendications 10 à 13, dans laquelle le mélange de pigments contient 25 à 40 % en poids de Pigment Rouge 177 du C.I. et 60 à 75 % en poids de Pigment Bleu 60 du C.I.
- 25
15. Composition selon l'une quelconque des revendications 1 à 14, qui contient 0,1 à 40 %, mieux encore 10 à 30 %, très préférablement environ 20 % de pigment, par rapport au poids de la dispersion.
16. Composition selon l'une quelconque des revendications 1 à 15, qui contient 0,1 à 30 %, de préférence 0,1 à 8 %, de dispersant, par rapport au poids de la composition.
- 30
17. Composition selon l'une quelconque des revendications 1 à 16, qui contient un biocide.
18. Composition selon l'une quelconque des revendications 1 à 17, dans laquelle le dispersant l'acide polyacrylique, l'acide polyméthacrylique, le poly(anhydride maléique), un polyuréthane, un éther de polyvinyle, l'alcool polyvinyle, un polyalkylène-glycol, le poly-(oxyde d'éthylène), des dérivés de cellulose, une polyimine, la polyvinylpyridine, ou leurs copolymères, ou des copolymères d'acide acrylique avec le styrène, l'acrylonitrile, l'acétate de vinyle, un vinylphosphonate, le propionate de vinyle, le chlorure de vinyle, l'acide itaconique ou l'anhydride maléique, ou des aminés grasses éthoxylées ou propoxylées, des sels quaternaires gras éthoxylés ou propoxylés, des amides gras éthoxylés, un alkyl-, cycloalkyl- ou alkylaryl-oxypoly(éthylénoxy)éthanol, un cycloalkyloxypoly(éthylénoxy)-laurate ou oléate, le laurate ou l'oléate de polyéthylène-glycol 400, un alkyl-, cycloalkyl-ou alkylaryl-poly(éthylénoxy)carboxylate ou phosphonate, ou un polymère d'acide sulfonique aromatique avec le formaldéhyde ou ses sels.
- 35
19. Procédé pour teinter du papier à utiliser pour un matériau d'emballage alimentaire, lequel procédé consiste à appliquer dans au moins un stade du procédé de fabrication de papier
- 45
- a) une composition selon la revendication 1,
  - b) une composition selon la revendication 10,
  - c) une dispersion aqueuse de Pigment Violet 19 du C.I. et une dispersion aqueuse de Pigment Bleu 15 du C.I., ou
  - d) une dispersion aqueuse de Pigment Rouge 177 du C.I. et une dispersion aqueuse de Pigment Bleu 15 du C.I. ou de Pigment Bleu 60 du C.I.
- 50
20. Procédé selon la revendication 19, dans lequel la composition est ajoutée au cuvier de mélange, à la pâte travaillée diluée, à la pâte travaillée épaisse ou, de préférence, à la pâte brute.
- 55
21. Procédé selon la revendication 19 ou la revendication 20, dans lequel la composition est ajoutée en une quantité de 5 à 1000 g par tonne, de préférence en une quantité de 10 à 400 g/tonne et très préférablement en une quantité

**EP 1 165 696 B1**

de 50 à 400 g/tonne.

22. Procédé selon l'une quelconque des revendications 19 à 21, dans lequel, on ajoute, de plus, un coagulant ou un adjuvant de rétention cationique.

5

23. Procédé selon la revendication 22, dans lequel le coagulant cationique est ajouté à la pâte travaillée épaisse, de préférence avant dilution.

10

24. Procédé selon la revendication 23, dans lequel le coagulant cationique est ajouté en une quantité de 10 à 1000 g par tonne, de préférence en une quantité de 50 à 700 g/tonne et très préférablement en une quantité de 100 à 500 g/tonne.

15

25. Utilisation d'une composition selon la revendication 1 ou la revendication 10, pour teinter du papier à utiliser pour un matériau d'emballage alimentaire.

20

25

30

35

40

45

50

55